

Victorian Ash Timber - Properties

Property	Value
Durability Class	Strength Group SD 3 & 4 Joint Group JD 3
Janka Hardness	4.9
Density @ 12%MC	650 ave (kg/m3)
AS 2796	Victorian Ash is seasoned to comply with the Australian Standard AS 2796 (9%-14%) with the average moisture content ranging between 10%-12%.
Grade	Select
Finish	Clear pre-treated, prepared for clear finish
Fire Indices	<i>Refer Australian Standard AS1530 Part 3 and Building Code of Australia.</i>
Ignitability index	14
Spread of flame index	8
Heat evolved index	7
Smoke development index	3
Critical Radiant Heat Flux	More than 2.2 kW/m2 and less than 4.5 kW/m2
Smoke Development Rate	Less than 750 %-min
Average extinction area	Less than 250m2/kg
Material Group No	3